GENERAL BUILDING PRODUCT DATA SHEET



General Product Information

Roxul stone wool products are made of basalt, a volcanic stone.

Roxul stone wool products are non-combustible with a melting point of approximately 1000°C. They are particularly suitable for thermal insulation, fire protection and sound reduction/absorption.

Roxul stone wool is inorganic and contains no nutritious

substance. Therefore it will not be attacked by microorganisms. Mineral wool will not rot and does not attract vermin.

No CFCs, HFCs, HCFCs, or asbestos are used in the manufacture of Roxul stone wool products.

ThermalRock B (Blanket)

Common applications

ThermalRock B is manufactured in a wide variety of thicknesses and densities to suit most requirements, suitable for general application in residential, commercial and industrial buildings.

Dimensions

Product type	Thickness (mm)	Length x Width (mm)		
B40	50	5000 x 1200		
	50	7500 x 1200		
B50	50 ′	5000 x 1200		
	50	7500 x 1200		
B60	25	10000 x 1200		
	50	5000 x 1200		
	50	7500 x 1200		
B80	25	8000 x 1200		
	25	10000 x 1200		
	50	5000 x 1200		
	50	7500 x 1200		
B100	25	5000 x 1200		
	25	8000 x 1200		
	50	2500 x 1200		
	50	4000 x 1200		

Note: Please contact your local representatives for the specific densities and thicknesses that are available locally.

Facings

ThermalRock B products are available in plain, aluminium foil facings and one-sided or two-sided glass tissue facings.

Packaging and storage

ThermalRock B is supplied in folded or roll form (depending on factory) and shrink-wrapped in polyethylene sheets for ease of handling, transportation, storage and identification. Products should be stored indoors or under a waterproof covering.



Technical parameters

Product types	B40	B50	B60	B80	B100	Standards
Nominal density (kg/m³)	40	50	60	80	100	
Thermal conductivity 20°C λ Values (W/mK)	0.037	0.036	0.036	0.036	0.036	ASTM C177/C518
Sound Absorption (BS EN 20354: 1993)	Please contact your local representative for more information					
Fire Performance	Non-combustible (without facing)					BS 476 Part 4/EN 13501-1
Water Vapour Absorption	Absorb less than 0.04%					ASTM C1104/C1104M
Water Absorption (partial immersion)	Less than 1kg/m²					EN 1609:97